

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



WO 2004/036302 A1

(43) International Publication Date
29 April 2004 (29.04.2004)

PCT

(10) International Publication Number
WO 2004/036302 A1

(51) International Patent Classification⁷: G02F 1/1337, 1/1335 (74) Agent: DAVIES, P.; D/IP QinetiQ Formalities, Cody Technology Park, A4 Building, Room G016, Ively Road, Farnborough, Hampshire GU14 0LX (GB).

(21) International Application Number:
PCT/GB2003/004483

(22) International Filing Date: 17 October 2003 (17.10.2003)

(25) Filing Language: English

(26) Publication Language: English


(30) Priority Data:
0224179.2 17 October 2002 (17.10.2002) GB
0225921.6 7 November 2002 (07.11.2002) GB

(71) Applicant (for all designated States except US): ZBD DISPLAYS LTD. [GB/GB]; Malvern Hills Science Park, Geraldine Road, Malvern, Worcs WR14 3SZ (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): AMOS, Richard, Michael [GB/GB]; ZBD Displays Ltd., Malvern Hills Science Park, Geraldine Road, Malvern, Worcs WR14 3SZ (GB). BRYAN-BROWN, Guy, Peter [GB/GB]; ZBD Displays Ltd., Malvern Hills Science Park, Geraldine Road, Malvern, Worcs WR14 3SZ (GB). JONES, John, Clifford [GB/GB]; ZBD Displays Ltd., Malvern Hills Science Park, Geraldine Road, Malvern, Worcs WR14 3SZ (GB). WOOD, Emma, Louise [GB/GB]; ZBD Displays Ltd., Malvern Hills Science Park, Geraldine Road, Malvern, Worcs WR14 3SZ (GB).

(54) Title: LIQUID CRYSTAL ALIGNMENT LAYER



WO 2004/036302 A1

(57) **Abstract:** This invention relates to a photopolymer mixture capable of use for a liquid crystal alignment layer and to an alignment layer formed from such a photopolymer mixture. The mixture comprises at least two polymerisable materials which are blended together in proportion so as to give a predetermined, preferably low, surface energy. A low surface energy, e.g. less than 4×10^{-2} N/m can result in an alignment layer which imparts a particular orientation to liquid crystal molecules without requiring any post cure treatments. The polymerisable materials may be monomers, oligomers or diluents that form long chain molecules when cured and the mixture may contain additives to lower the overall surface energy.